

Platten- dicke mm	Press-Breite α : Werk Arnberg; g : Werk Gotha; [..]: kein-Standard mm				Gewicht									
					VT		VL		VV		Sonstige			
					kg/m ²	kg/m ³	kg/m ²	kg/m ³	kg/m ²	kg/m ³	Typ	kg/m ²	kg/m ³	
Vollspanplatten														
10	1220	1250 _g		2020 _α			5,6	560	6,6	660				
10,6	1220	[1880]		2020 _g			5,9	560	6,7	630				
11	1220 _α			2020			6,2	560	6,9	630				
12	1220	1880		2020 _g			6,7	560	7,8	650				
13	1220			2040 _g			7,3	560	8,4	645				
13,5				2040 _g			7,6	560						
14,3				2040 _g			8,0	560						
16		1880		2020 _g			8,3	520						
16,5		[1880]	2020	[2070]			8,6	520	10,4	630				
19			1978 _g			8,0	420	9,9	520					
25		[1250]		2070 _α			13,0	520	15,8	630	VS	13,5	540	
28	[955]	1270 _α	[1880]	1975	2042	11,8	420	14,0	500	17,6	630	VS	15,1	540
32	1265	1880 _α	1888 _g	[1940]	2090 _α	13,4	420	15,7	490	9,2	600			
33	1265	1880	1958	[2000]	2090	13,9	420	16,2	490	19,8	600	VS	17,8	540
33,5	1265 _α		1958 _g	2090 _g		14,1	420	16,4	490					
34	1260 _α	[1265]	[1880]	1958 _g	2090	14,3	420	16,7	490	20,4	600			
35		[1880]	[1958]			14,7	420	17,5	490	21,0	600	VS	18,2	520
38			1920	1978		16,0	420	18,6	490	23,6	620	VE	20,1	530
												VE1	19,4	510
												VE7	17,9	470
42				1978				20,6	490					
							HVA		HVB					

Rahmenholz „HOMOGEN“

28				2042 _α		8,2	650							
32	1880 _α			2040 _α	2090 _α	20,8	650	22,4	700					
33		1958 _α	[2000]	2040 _α	2090 _α	21,5	650	23,1	700					
34					2090 _α	22,1	650	23,8	700					

Presslänge

bei Pressbreite ≤ 1270 mm : 600 - 3000
 bei Pressbreite > 1270 mm : 600 - 1200